

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar  
İstanbul/ TÜRKİYE

**TEST REPORT  
DENEY RAPORU**



**Customer name:** DOTEKS TEKSTİL GIDA SAN.TİC.LTD.ŞTİ.  
**Address:** Mahmutbey Mah. İnönü Cad. No:157 Özyurt Plaza A1 Blok Kat:2 İstoç –  
Bağcılar /İSTANBUL  
**Buyer name:**  
**Contact Person:** ZELİHA AĞAOĞLU  
**Order No:**  
**Article No:** PROTECTIVE DRAPE FABRIC P393  
**Name and identity of test item:** BLUE NON-WOVEN + FILM 49gr  
**The date of receipt of test item:** 11.06.2020  
**Re-submitted/re-confirmation date:** -  
**Date of test:** 11.06.2020-12.06.2020  
**Remarks:** -  
**Sampling:** The results given in this report belong to the received sample by vendor.  
**End-Use:** -  
**Care Label:** Not specified.  
**Number of pages of the report:** 3

*The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.*

*EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.*

*The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.*

Seal  
Date  
12.06.2020

Customer Representative  
Zahide TAPAN

Head of Testing Laboratory  
Sevim A. RAZAK  
12.06.2020

This report shall not be reproduced other than in full except with the permission of the laboratory.  
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.


AB-0583-T

20018722

06-20

REQUIRED TESTS	RESULT	COMMENTS
<b>PHYSICAL PROPERTIES</b>		
Water Permeability	P	
Water Resistance (Impact Penetration)	P	
P: Pass F: Fail R: Refer to retailer technologist. Evaluation was performed according to the AAMIPB70 guidelines.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor  $k=2$ , providing a level of confidence of approximately 95 %. Tests marked (\*) in this report are not included in the accreditation schedule.



Gen.f136-2/03

This report shall not be reproduced other than in full except with the permission of the laboratory.  
*Testing reports without signature and seal are not valid.*

AB-0583-T

20018722

06-20

## TEST REPORTS

### WATER PERMEABILITY; AATCC 127:2017-OPTION 2

Hydrostatic Head Tester, Textest marka Fx 3000 model  
Temperature of water 20°C. Pressure increase ratio 10 mbar/dk.  
Performed in the conditioned room (21±2°C-65%±5)

	<u>RESULT</u>	<u>REQUIREMENT</u>
Sample 1	383.5 cm SS	≥ 50 cmSS (Level 3)
Sample 2	352.9 cm SS	
Sample 3	390.7 cm SS	
Average	375.7 cm SS	

### WATER RESISTANCE-IMPACT PENETRATION TEST; AATCC 42:2017(\*)

Test samples were conditioned for at least 4 hours prior to testing (65 ± 5% RH, 21 ± 2 ° C).  
Water temperature : 27±1°C  
Amount of sprayed water: 500 ml

	<u>RESULT</u>	<u>REQUIREMENT</u>
Water penetration (g)	0 g	≤1,0 g (Level 3)